

Test Report No: 230824C

Slip Resistance Measurement of New Pedestrian Surfaces: AS4586:2013 Appendix A

Client: Stone Depot - 181-187 Cowpasture Road, Wetherill Park NSW 2164

Test Date: 23/08/2024 **Temperature:** 23 Deg C.

Test Conducted to: AS 4586:2013 Appendix A **Conducted by:** Sean C Murphy
B.A (U. Syd), Dip. Ed

Test Method: Wet Pendulum Testing **Test Device:** Munro - Serial No. 201!
Calibration Exp. 11/1/2025

Surface: Crema Sienna – Sandblasted & Tumbled - Pavers, Tiles, Crazy Paving, Cobbles & Batons **Rubber Slider Used:** Slider 96 (4 S Rubber)

Slider Preparation: Abrasive paper, Grade P400 followed by pink lapping paper wet

Test Location: Stone Depot - 181-187 Cowpasture Road, Wetherill Park NSW 2164

Surface Preparation: Cleaned with Water & Hand Scrubbing

Surface Application: N/A

Tested Area:

Specimen Number	Location	Condition	Gradient %	Direction of Test	Mean BPN Last 3 swings
1	Loose Sample	As Found	<2.0	N/A	60
2	Loose Sample	As Found	<2.0	N/A	60
3	Loose Sample	As Found	<2.0	N/A	58
4	Loose Sample	As Found	<2.0	N/A	59
5	Loose Sample	As Found	<2.0	N/A	58

Mean BPN Slip Resistance Value - SRV **59**

Classification **P5**

Contribution to Risk **Very Low**

Interpretation of the Wet Pendulum Results

Classification of pedestrian surface materials according to	Mean BPN
P5	>54
P4	45-54
P3	35-44
P2	25-34
P1	12-24
P0	<12

The AS 4586 standard provides a guide & recommendation for use, we recommend that this report be read in conjunction with AS 4586 & Handbook HB198: 2014. Refer to Table 3B of HB 198 for requirements of sloped surfaces & ramps. The results in this test do not account for any future wear, contamination or maintenance of this surface. Griptek Anti-Slip Solutions Pty Ltd or our agents, licencees or employees accept no responsibility for any actions whatsoever which may arise as a result

Approved Signatory: Michael Holt

