

Test Report No: 200625D

Slip Resistance Measurement of New Pedestrian Surfaces: AS4586:2013 Appendix A

Client: Stone Depot - 181-187 Cowpasture Road, Wetherill Park NSW 2164

Test Date: 20/06/2025 Temperature: 18 Deg. C

Test Conducted to: AS 4586:2013 Appendix A Conducted by: Sean C Murphy
B.A (Syd. U), Dip. Ed

Test Method: Wet Pendulum Testing Test Device: Munro - Serial No. 2015
Calibration Exp. 9/1/2026

Surface: Honey Jesper Granite – Exfoliated Rubber Slider Used: Slider 96 (4 S Rubber)
Tiles, Pavers, Crazy Pavers, Cobblestones, Batons Cert. No. 96/232/24, BN:45

Slider Preparation: Abrasive paper, Grade P400 followed by pink lapping paper wet

Test Location: 181-187 Cowpasture Road, Wetherill Park NSW 2164

Surface Preparation: Cleaned with Water & Hand Scrubbing

Surface Application: N/A

Tested Area:

Specimen Number	Location	Condition	Gradient %	Direction of Test	Mean BPN Last 3 swings
1	Loose Sample	As Found	<2.0	N/A	65
2	Loose Sample	As Found	<2.0	N/A	66
3	Loose Sample	As Found	<2.0	N/A	64
4	Loose Sample	As Found	<2.0	N/A	64
5	Loose Sample	As Found	<2.0	N/A	64

Mean BPN Slip Resistance Value - SRV 65

Classification P5

Interpretation of the Wet Pendulum Results	
Classification of pedestrian surface materials according to the AS 4586	Mean BPN
P5	>54
P4	45-54
P3	35-44
P2	25-34
P1	12-24
P0	<12

The AS 4586 standard provides a guide & recommendation for use, we recommend that this report be read in conjunction with AS 4586 & Handbook HB198: 2014. Refer to Table 3B of HB 198 for requirements of sloped surfaces & ramps. The results in this test do not account for any future wear, contamination or maintenance of this surface. GripTek Anti-Slip Solutions Pty Ltd or our agents, licencees or employees accept no responsibility for any actions whatsoever which may arise as a result of this test report, all information within this report is copyright & is protected by copyright law.

Approved Signatory: Michael Holt

